

**Technical data sheet**

**Quick-Step Variano**

Edition	01.2013	Norm	Parameters	Norm requirements	Quick-Step values
<b>Dimensions</b>					
Panel					2200x190 mm
overall thickness					14,0 mm
panels per pack					6
m <sup>2</sup> per pack					2,5080 m <sup>2</sup>
<b>Panel construction</b>					
Surface layer			PEFC, FSC or legally controlled sources		3,0 mm
Coreboard				Spruce or Pine	Hevea QS Mastercore
Backing layer			PEFC, FSC or legally controlled sources		2,00 mm
Tongue and groove			Lengthwise Width		Uniclic Uniclic Multifit
<b>Surface layer</b>					
wood species				Oak	
origine				Europe	
finishing					crf catalogue/website
grading					crf catalogue/website
<b>Installation</b>					
floating			on Quick-Step underlay	cf installation instructions	
glued to subfloor			Quick-Step MS polymere resin	cf installation instructions	
<b>CE</b>		EN 14342:2008	notified body	DAP-PL-1033.00	level 4
<b>PEFC</b>					PEFC label
<b>Warranty</b>					lifetime lifetime on request
<b>Finishing</b>					
Wear resistance		UV-curing oil SIS 923509 DIN 68861	falling sand S33 anti-scratch Top Coat with nano-technology		2 lagen 800-1000 100-1050
Scratch resistance		EN 13442		all except blue ink blue ink	class 5 class 3
Stain resistance					
<b>General aspect of installed flooring</b>		EN 13489	lippings - difference in height difference in width cupping lengthwise cupping in width	≤ 0,20 mm ≤ 0,20 mm ≤ 0,1% ≤ 0,2 %	≤ 0,15 mm ≤ 0,15 mm ≤ 0,1 % ≤ 0,2 %
<b>Castor chairs</b>				use soft castors Type W (EN 12529) and/or suitable office mat	
<b>Slip resistance</b>		CEN/TS 15676			USRV 50-52
<b>Formaldehyde emission</b>		EN 717-1			E1
<b>PCP</b>					below detection limit
<b>Heat resistance</b>		EN 12664			0,127 m <sup>2</sup> .°K/W
<b>Underfloor heating</b>				consult special installation instructions	
<b>Reaction to fire</b>		EN 14342	CWFT		D <sub>fl</sub> - S <sub>1</sub>
			With an oak toplayer		C <sub>fl</sub> - S <sub>1</sub>

UNILIN Flooring bvba - Ooigemstraat 3 - 8710 Wielsbeke - België  
 E-mail: technical.service@quick-step.com Tel : +32 56 67 52 37 Fax : +32 56 67 52 39